

CARBO S 21

Standards

DIN 8555	E 20-UM-300-CKTZ
----------	------------------

Approvals ---

Characteristics AC-weldable hardfacing electrode with an alloyed core and a recovery of 160 %. The deposit is a cobalt base alloy of high tenacity as well as extreme corrosion- and heat resistance. The weld metal is highly resistant to impact and is work-hardening up to 45 HRC. Working temperature should be kept between 400° and 600°C, depending on base material and type of construction. Slow cooling, if necessary oven cooling, is recommended for low alloyed and austenitic steels. Subsequent heat treatment (stress relief at 700°C approx.) is not necessary, except on large structures.

Operating temperature From room temperature up to + 300° C

Typical applications Due to its above-mentioned characteristics CARBO S 21 is particularly recommended for use on all work pieces which are subject to corrosion, impact wear as well as high temperatures or thermal shocks.

Hardness of all-weld metal (typical values)	At Rt. HRC	+ 300°C HB	work hardened HRC	Melting- point	Density g/cm ³
	ca. 30	ca. 280	ca. 280	1250°C	8,3

Weld metal analysis (typical, wt. %)	C	Si	Mn	Cr	Mo	Ni	Co	Fe
	0,3	0,9	1	28	5,5	3	Base	3

Current = + / ~ 42 V

Welding positions PA, PB, PC

Rebaking 1 h, 350 + / - 10 °C (if required)

Flux-cored wire equivalent

CARBO F- S 21

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,5 x 350	50 - 60	145	580	34,5	5,0	20,0
3,2 x 350	90 - 130	84	336	59,5	5,0	20,0
4,0 x 350	120 - 170	62	247	81,0	5,0	20,0
5,0 x 350	150 - 200	38	152	131,2	5,0	20,0