

CARBO 4431 MPR

International standards	Material No.	1.4431
	EN 1600	E 20 10 3 L R 53
	AWS A 5.4	E308MoL-17

Approvals ---

Characteristics and typical applications

CARBO 4431 MPR is an AC-weldable, rutile coated electrode with a recovery of 160%, suitable for joining corrosion-proof CrNiMo steels of low carbon content as well as stabilised and non-stabilised steels of identical or similar characteristics which are resistant to chemical agents. Especially on base materials which are at a risk of cracking, The electrode can be used for joining austenitic to ferritic steels. Same suitability for joint welding heat treatable steels, stainless Cr-steels, manganese steels, screening steels to each other and to dissimilar steel types.

Operating temperature - 60° C up to + 300° C

Base materials Dissimilar joints of 1.4583 with H I / H II, 17Mn 4, StE 355
1.4583 with P235GH / P256GH, P295GH, P355N

1.4404 X2CrNiMo17-13-2	1.4436 X3CrNiMo17-13-3
1.4435 X2CrNiMo18-14-3	1.4408 GX5CrNiMo19-11-2
1.4409 X2CrNiMo18-11-2	1.4571 X6CrNiMoTi17-12-2
1.4429 X2CrNiMo17-13-3	1.4583 (G)X10CrNiMoNb-18-12
1.4401 X5CrNiMo17-12-2	

Mechanical properties of all-weld metal

(typical values)

Tensile strength R_m N/mm ²	Yield strength $R_{p0,2}$ N/mm ²	Elongation A_5 %	Impact strength ISO – V J at - 60° C
700	540	30	50

Weld metal analysis %
(typical wt %)

C	Si	Mn	Cr	Ni	Mo
< 0,04	0,8	0,7	19	10	3

Current = + / ~ / 50 V

Welding positions PA, PB

Rebaking 1 h, 350° C + / - 10° C (if necessary)

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,0 x 300	40 - 75	230	920	17,4	4,0	16,0
2,5 x 350	65 - 95	157	629	31,8	5,0	20,0
3,2 x 350	90 - 130	93	372	53,7	5,0	20,0
4,0 x 450	120 - 180	57	229	104,6	6,0	24,0
5,0 x 450	170 - 240	37	147	163,4	6,0	24,0